

Nylene® BS-700-A

TECHNICAL DATASHEET

TDS Ref # 172 Reviewed: 7/24/2013

DESCRIPTION

- Spinning Grade Polymer-Medium Dye

PROPERTIES

MANUFACTURING SPECIFICATIONS	Unit	Minimum	Maximum	Plant Test Method
Methanol Extractables	(%)		.80	2-3
Moisture Content	(%)		.12	2-2A
Relative Viscosity (2)	(96% Sulphuric Acid 68°F)	2.62	2.78	2-5

NOTES

- Net 1,764 lb of polymer in a 6-mil PE liner within a corrugated octobox. Pallets can be supplied as required.

CHARACTERISTICS

Resin Type: Nylon 6

Product Characteristics:

Unreinforced, Differential Dye, Medium Dye

EXTRUSION PROCESSING

Fiber Extrusion

MARKETS USED

- Carpet Fiber

APPLICATIONS

- Commercial Carpet Fiber
- Residential Carpet Fiber

DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



Headquarters and Facility:

55 Haul Road, Wayne, NJ 07470
P: 973-694-4141 | F: 973-694-3549

North American Sales Office:

31700 Telegraph Rd. Suite 235, MI 48025
P: 248-377-6769 | F: 248-377-3845

Nylene Custom Resins Facility:

1421 Hwy 136 W. Henderson, KY 42420
P: 270-826-7641 | TF: 800-626-7050

Nylene Canada Facility

200 McNab Street, Arnprior ON, K7S 3P2
P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:

www.nylene.com/contactus

www.nylene.com | info@nylene.com

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.